

## SPECIFICATIONS

Commercial 5754

PLANCAST PLUS Plate is available:

- > In thicknesses from 5mm to 100mm
  - > Standard Width 1520mm
  - > Standard Lengths 3020mm or 4000mm
- It is also available in cut pieces

## CHEMICAL COMPOSITION

PLANCAST PLUS  
5754 Plate

Element	% Present
Magnesium (Mg)	2.60 - 3.60
Manganese (Mn)	0.0 - 0.50
Iron (Fe)	0.0 - 0.40
Silicon (Si)	0.0 - 0.40
Chromium (Cr)	0.0 - 0.30
Zinc (Zn)	0.0 - 0.20
Titanium (Ti)	0.0 - 0.15
Copper (Cu)	0.0 - 0.10
Aluminium (Al)	Balance

## SUPPLIED FORMS

- Plate

## GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.66 g/cm <sup>3</sup>
Melting Point	600 °C
Thermal Expansion	24 x10 <sup>-6</sup> /K
Modulus of Elasticity	70 GPa
Thermal Conductivity	140-160 W/m.K
Heat Capacity	900 J/kgK
Electrical Conductivity	17-23 MS/m

## MECHANICAL PROPERTIES

PLANCAST PLUS 5754  
Plate  
5mm - 100mm thick

Property	Value
Proof Stress	90 Min MPa
Tensile Strength	200 Min MPa
Elongation A50 mm	12 Min %
Hardness Brinell	55 Min HB

## CONTACT

Web: [www.dalsteel.com.au](http://www.dalsteel.com.au)

## REVISION HISTORY

Datasheet Updated 09 April 2019

## DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.